


Technical sheet BZ9871262






Esagono Graphite


Its hexagonal shape generates an interesting and trendy pattern when covering a certain space. It is a very modern mosaic, which is not only elegant but also youthful and fresh. Its shape at the level of architecture and design is perfect to make the most of the space with the minimum material to make your spaces shine.



www.brezzadesign.it









## Texture

As it is a porcelain material, in its purest composition, it has a very organic texture that is pleasant to the touch and very subtle to the eye. ESAGONO TUTTOSPESSORE mosaic by BREZZA Design Italy has an ideal matte finish for your spaces.





The Graphite is nothing more than the absence of the other colors, it is the lack of light. Represents strength and elegance in addition to the drama within the interior, it can be used as a striking element within the design of the space, as well as highlight in small details. It is a bold and daring color, but always very elegant.

www.brezzadesign.it

REZZA



SPECIFICATION	TEST METHODS		REQUIREMENTS IN ACCORDANCE TO THE STANDARDS		BREZZA AVERAGE VALUE
WATER ABSORPTION	ISO 10545-3	≤ 0,5%		≤ 0,2%	
FLEXURAL RESISTANCE	ISO 10545-4		Min./MNH 35 N/mm <sup>2</sup>		Min./MNH 40 N/mm2
MODULUS OF RUPTURE	ISO 10545-4	THICKNESS ≥ 7,5mm: min. 1300 N		THICKNESS ≥ 7,5mm: min. 1300 N	
DEEP ABRASION RESISTANCE	ISO 10545-6		≤ 175 mm <sup>3</sup>		≤ 175 mm3
RESISTANCE TO SURFACE ABRASION	ISO 10545-7		CLASSES 0-5		CLASSES 0-5
LINEAR EXPANSION THERMIC COEFFICIENT	ISO 10545-8		AVAILABLE ON REQUEST		INSIGNIFICANT
RESISTANCE TO SUDDEN TEMPERATURE CHANGES	ISO 10545-9		AVAILABLE ON REQUEST		YES
FROST RESISTANCE	ISO 10545-12		ALWAYS TESTED – EXIGEE		ALWAYS TESTED - EXIGEE
HOUSEHOLD CHEMICALKS AND SWIMMING POOL WATER CLEANSERS	ISO 10545-13	UGL GL UGL GL	min. UB MNH. UB min. GB MNH. GB FROM ULA, ULB TO ULC - DE ULB A ULC FROM GLA, GLB TO GLC - DE GLA, GLB A GLC	UGL GL UGL	min. UB MNH. UB min. GB MNH. GB FROM ULA, ULB TO ULC- DE ULB A ULC FROM GLA, GLB TO GLC- DE GLA, GLB A GLC
ACIDS AND LOW CONCENTRATION ALKALIS	ISO 10545-13	UGL GL UGL GL	min. UB MNH. UB min. GB MNH. GB FROM ULA, ULB TO ULC - DE ULB A ULC FROM GLA, GLB TO GLC - DE GLA, GLB A GLC	UGL GL UGL GL	min. UB MNH. UB min. GB MNH. GB FROM ULA, ULB TO ULC - DE ULB A ULC FROM GLA, GLB TO GLC - DE GLA, GLB A GLC
ACIDS AND HIGH CONCENTRATION ALKALIS			AVAILABLE ON REQUEST		AVAILABLE ON REQUEST
STAIN RESISTANCE	ISO 10545-14		AVAILABLE ON REQUEST		STAIN RESISTANCE
COLOURS STABILITY TO LIGHT	DIN 51094	THEY	Ó DO NOT HAVE TO SHOW VISIBLE COLOUR ALTERATION	STA	ABLE IN OUTDOOR AND INDOOR CONDITIONS

www.brezzadesign.it



21-2



★ AFRICAN STYLE

TASCHEN

www.brezzadesign.it